

PVC SCHEDULE 40 PRESSURE/DWV PIPE

Size	Outside Diameter	Insider Diameter	Wall Thickness	Weight Per Foot	Pressure Rating	Pipe Stiffness	Bell Length
1/2"	0.840	0.609	0.109	0.164	600	5,928	1.00
3/4"	1.050	0.810	0.113	0.218	480	3,136	1.25
1"	1.315	1.033	0.133	0.324	450	2,547	1.50
1-1/4"	1.660	1.363	0.140	0.439	370	1,397	1.75
1-1/2"	1.900	1.593	0.145	0.525	330	1,008	2.50
2"	2.375	2.049	0.154	0.705	280	596	2.75
2-1/2"	2.875	2.445	0.203	1.118	370	784	2.00
3"	3.500	3.042	0.216	1.463	260	509	4.00
4"	4.500	3.998	0.237	2.083	220	307	4.75
6"	6.031	6.031	0.280	2.822	180	205	6.50

*1-1/2", 2", 3", 4", and 6" is dual-rated for Pressure & DWV applications

SPECIFICATIONS:

Product Standard	<u>Pressure:</u> ASTM D1785, NSF/ANSI 14, ANSI/NSF 61 <u>Dual-Rated:</u> ASTM D1785, ASTM D2665, NSF/ANSI 14, ANSI/NSF 61
Material Standard	ASTM D1784 PVC 1120 Cell Class 1-2-4-5-4
Class/Type	Schedule 40, Iron Pipe Size (IPS)
End Finish	Plain End & Belled End
Listing	ICC-ES File PMG-1545

